


INFORMATIVE NOTE
Name: REFLEXX R94
Date: 05/10/2024 Rev: 06
MANUFACTURER

 REFLEXX SpA
 Via Passeri, 2 46019 VIADANA (MN)
 Tel.: + 39 0375 758891 Fax + 39 0375
 464504 info@reflexx.com
www.reflexx.com
Pack

Cod./Size	Box	Carton
R94/S	8032891632741	8032891637746
R94/M	8032891632758	8032891637753
R94/L	8032891632765	8032891637760
R94/XL	8032891632772	8032891637722

DESCRIPTION: ■ reusable glove ■ **Material:** latex ■ **Shape:** five fingers, beaded dripless ■ **Colour:** bicoloured, blue and yellow ■ **Feature:** soft cotton flock lining inside and anti-slip pattern on the outer surface ■ **Packing:** 1 pair / envelope; 50 bags / carton ■ **ISO 2859:** AQL 1.5 (level G1)

CONFORMITY AND PERFORMANCES


Personal Protective Equipment cat III 0465 ANCI_CIMAC, Via Aguzzafame, 60/b 27029 Vigevano (PV)
 Reg EU 2016/425 - EN ISO 374-1:2016 TYPE B - EN ISO 374-5:2016 - EN 374-2:2014 - EN 420:2003 + A1 2009 - EN 388:2016+A1:2018






Reg CE 1935/2004 – Reg EU 10/2011 - DM 21/03/73. To such use carefully read the declaration of suitability for food contact (DICA).

DIMENSIONS		
Cod./Size	Length mm (± 5)	Width mm (± 3)
R94/S (7)	300	95
R94/M (8)	300	107
R94/L (9)	300	113
R94/XL (10)	300	118

Thickness mm	Palm (±0.05)	0.5
--------------	--------------	-----

EN 455-2:2009/A1	Tensile strength	≥6 N
------------------	------------------	------

EN ISO 374-1:2016				
Chemical compound:	COD	EN 16523-1:2015 TYPE B		EN 374-4:2013
		Performance level	Breakthrough time	% degradation
Sodium hydroxide 40%	K	3	>60'	27.2%
Hydrogen peroxide 30%	P	3	>60'	18.3 %
Formaldehyde 37%	T	3	>60'	10.9%
Nitric acid 65%	M	3	>60'	89.2%



EN 388:2016+A1:2018				
Test:	Results:		Requirements:	
	Level:			
Abrasion	0	Breakage at 100 cycles	Level 1 Level 2 Level 3 Level 4	100 cycles 500 cycles 2000 cycles 8000 cycles
Cut	1	Minimum Index = 1.4	Level 1 Level 2 Level 3 Level 4 Level 5	Index = 1,2 Index = 2,5 Index = 5,0 Index = 10,0 Index = 20,0
Tear	2	Minimum recorded value = 27 N	Level 1 Level 2 Level 3 Level 4	10 N 25 N 50 N 75 N
Perforation	0	Minimum recorded value = 10 N	Level 1 Level 2 Level 3 Level 4	20 N 60 N 100 N 150 N

RISKS FROM WHICH THE DPI IS DESIGNED TO PROTECT:

COD		Protection
K Sodium hydroxide 40%	CAS:1310-73-2	Protection from use of inorganic bases
P Hydrogen peroxide 30%	CAS: 7722-84-1	Protection from use of peroxides
T Formaldehyde 37%	CAS: 50-00-0	Protection from the use of aldehydes
M Nitric acid 65%	CAS: 7697-37-2	Protection from use of mineral acids

Test	Results
Cut	1
Tear	2

RECOMENDATIONS OF USE Multi-purpose glove to protect the hand and/or the handled product, can also be used for general uses ■ The glove is suitable for contact with pure chemical products for a period of less than the permeation time indicated in the chemical resistance table ■ Results obtained under laboratory conditions may not reflect actual working time **WARNINGS** Before using the product, try it in the real condition of use ■ The glove is a device subject to wear, so frequent replacement is recommended and in all cases where imperfections are observed ■ Wear gloves with dry, clean hands ■ The product contains natural latex which can cause allergic reactions of type I and IV hypersensitivity. In case of reaction, discontinue use and consult a doctor ■ Do not use gloves when there is a risk of getting caught in the moving parts of machinery **STORAGE AND DISPOSAL** Store the gloves in their original packaging in a dry place ■ Store at room temperature ■ Do not expose to direct sunlight and heat sources ■ Do not reuse contaminated gloves. Rinse with water and dry after use ■ Re-laundered gloves reduce performance resistance against chemicals. Manufacturer will not be responsible for the performance ■ The expiry date is 3 years from the date of manufacture indicated on the sales package, and is valid for the product properly stored ■ Gloves must be disposed of according to local regulations ■ Declaration of Conformity on www.reflexx.com