



## INFORMATIVE NOTE

Name: REFLEXX N79plus

Date: 21/10/2021 Rev: 04

### MANUFACTURER

REFLEXX SpA  
Via Passeri, 2 46019 VIADANA (MN)  
Tel.: + 39 0375 758891 Fax + 39 0375  
464504 [info@reflexx.com](mailto:info@reflexx.com)  
[www.reflexx.com](http://www.reflexx.com)



Cod./Size	Box	Carton
N79P/S	8032891633533	8032891638538
N79P/M	8032891633540	8032891638545
N79P/L	8032891633557	8032891638552
N79P/XL	8032891633564	8032891638569

**DESCRIPTION** ■ disposable examination glove powder free, non sterile ■ **Material:** nitrile ■ **Shape:** ambidextrous; five fingers, beaded cuff; long cuff ■ **Colour:** black ■ **Feature:** internally chlorinated; textured surface and textured fingertips ■ **Packing:** 50pieces/box; 10 boxes/carton ■ **ISO 2859:** AQL 1.5 (level G1) freedom from holes; AQL 2.5 (level G1) major defects; AQL 4 (level G1) minor defects

### CONFORMITY AND PERFORMANCES

#### Personal Protective Equipment cat III

0465 ANCI\_CIMAC, Via Aguzzafame, 60/b 27029 Vigevano (PV)

Reg EU 2016/425 - EN ISO 374-1:2016 TYPE B - EN ISO 374-5:2016 - EN 374-2:2014 - EN 420:2003 + A1 2009

#### Medical Device

Reg EU 2017/745 - EN 455 1,2,3 & 4


(CND T01020204 NON SURGICAL NITRILE GLOVES)



cat III  
class I

DIMENSIONS		
Cod./Size	Length. min(mm)	Width (±5 mm)
N79P/S (7)	300±20	85
N79P/M (8)	300±20	95
N79P/L (9)	300±20	105
N79P/XL (10)	300±20	115

Thickness mm	Palm (+/- 0.03)	0.14
EN 455-2:2009/A1	Tensile strength	≥6 N



EN ISO 374-1:2016				
Chemical compound:	COD	EN 16523-1:2015 TYPE B		EN 374-4:2013
		Performance level	Breakthrough time	% degradation
Sodium hydroxide 40%	K	3	>60'	59.0%
Hydrogen peroxide 30%	P	3	>60'	9.1%
Formaldehyde 37%	T	3	>60'	3.5%
n-Heptane	J	2	>30'	34.6%

#### RISKS FROM WHICH THE DPI IS DESIGNED TO PROTECT:

COD		Protection
K Sodium hydroxide 40%	CAS:1310-73-2	Protection from use of inorganic bases
P Hydrogen peroxide 30%	CAS: 7722-84-1	Protection from use of peroxides
T Formaldehyde 37%	CAS: 50-00-0	Protection from the use of aldehydes
J n-Heptane	CAS: 142-82-5	Protection from the use of saturated hydrocarbons

**RECOMENDATIONS OF USE** Multi-purpose glove to protect the hand and/or the handled product, can also be used for general uses ■ The glove is suitable for contact with pure chemical products for a period of less than the permeation time indicated in the chemical resistance table ■ Results obtained under laboratory conditions may not reflect actual working time **WARNINGS** Before using the product, try it in the real condition of use ■ The glove is a device subject to wear, so frequent replacement is recommended and in all cases where imperfections are observed ■ Wear gloves with dry, clean hands ■ In rare cases where transient hypersensitive skin reactions may occur, discontinue use and consult a doctor ■ The user must inform the manufacturer and the relative authority of any incidents occurring during the use of the protective equipment ■ Do not use gloves when there is a risk of getting caught in moving machine parts **STORAGE AND DISPOSAL** Store the gloves in their original packaging in a dry place. ■ Do not expose to direct sunlight and heat sources. ■ The expiry date is 3 years from the date of manufacture indicated on the sales package, and is valid for the product properly stored ■ Gloves must be disposed of according to local regulations ■ Declaration of Conformity on [www.reflexx.com](http://www.reflexx.com)